

- •634 Route 228 P.O. Box 599 Mars, PA. 16046 724-625-3116 FAX 724-625-1640
- •4111 Walden Ave Lancaster, NY 14086 716-681-1581 FAX 716-681-1513
- •900 W. Smith Rd. Medina, OH 44256 330-723-7780 FAX 330-723-7780
- •7301 Bessemer Avenue Cleveland, OH 44127 216-341-2000 FAX 216-341-5833





WEATHERPROOF™ Asphalt Fibered Roof Coating #10105

A tough, high quality coating manufactured with specially selected asphalts, fibers, and a surfactant It applies easily by brush or spray and displays unusually strong bonding and penetrating qualities. Applied as directed, it cures to a durable, weatherproof roof surface with excellent long-term flexibility. It increases roof service life and helps preserve old, dried out roof surfaces. Meets all the requirements of ASTM D4479.

Uses

- A weatherproof surface coating for built up or composition roofs.
- A weatherproof surface coating for metal roofs.
- A weatherproof surface coating for roof masonry surfaces and gutters.
- A reinforced, below ground dampproofing coating for concrete and masonry surfaces.

<u>Advantages</u>

- · Ready to use
- Internally reinforced fills and bridges hairline cracks.
- Seals oils in and water out preserving roof surface.
- Remains flexible as it resists dirt, sun, wind, rain, ice, and snow.

INSTALLATION

Coverage

- Product yield to achieve desired rate is 2 to 4 gallons per 100 square feet. Yield varies according to the existing surface texture. As a general rule, the smoother the surface, the less material is required.
- Recommended application rate is 32 to 64 mils wet film thickness which will produce 24 to 48 mils dry. A
 mil is 1/1000 of an inch.

Surface Preparation

Remove all dirt, dust, rust, debris and water by brooming or pressure washing where necessary and where no danger or nuisance is caused to areas adjacent to work. All loose gravel must be removed from ballasted roofs. Scrape back to a hard edge all loose or scaled coating. Make all necessary repairs to existing surface prior to coating. Split seams, blisters, and cracks in existing surface and flashings should be repaired with **WEATHERPROOF**TM Roof Cement. Heavily weathered or exposed felt surfaces, as well as concrete, masonry, or rusted metal should receive an application of **WEATHERPROOF**TM Asphalt Primer prior to coating. All surfaces must be dry prior to application.

Application

- Apply by spray with a standard mastic pump and gun sized by a knowledgeable pump dealer for the
 particular application or by pouring directly from the container and spreading with a standard roofing
 brush. Be sure to spread product evenly.
- Clean up with mineral spirits, but do not thin the product with this or any other solvent.
- If the product is difficult to spread in cooler temperatures, warm containers by storing them overnight in a room at 65° to 75° F.

Drying Time

Four hours to touch at 70° F. and 50% relative humidity. Allow 7 to 14 days before exposure to foot traffic.

Restrictions

- Do not use with PVC film.
- Do not use where material, once applied, may come into contact with potable water.
- Not for use on or with products containing coal tar.
- Do not use on slate shingles or apply directly to wood surfaces.
- Not for use over rubber or plastic membranes asphalt modified only.
- Make certain surfaces to be coated are dry and clean and remain so for 24 to 48 hours after application.
- · For exterior use only.

Cautions

This product is combustible. Keep away from heat, sparks, and open flame. Avoid breathing of vapors.
 Avoid repeated or prolonged contact with skin. If swallowed, do not induce vomiting. Contact Physician immediately. Keep container closed when not in use. KEEP AWAY FROM CHILDREN. Product label and Material Safety Data Sheet contain further information on the safe use of this product and precautions for the safe disposal of the container. They should be read and understood prior to use.

SPECIFICATIONS

| Percent Solids by Weight | 75% |
|---|-------------|
| Percent Solids by Volume | |
| Weight Per Gallon: Pounds | |
| Flash Point - minimum | |
| Viscosity at 77° F | 22,500 cps. |
| Long-Term Service Temperature | |
| Water Resistance: Intermittent Exposure | |
| Water Resistance: Ponded | Fair |
| Solvent Resistance | Poor |
| U.V. Resistance | Good |
| VOC | < 250 g/l |
| | · · |

PACKAGING INFORMATION

| D. I. (N | 0: | 0 | 187.1.1.4 | |
|----------------|-------------|-----------------|---------------|---|
| Product Number | <u>Size</u> | <u>Quantity</u> | <u>Weight</u> | ı |
| 10155 | 55 gal. | Each | 500 lbs. | ļ |
| 10105 | 5 gal. | Each | 45 lbs. | ļ |
| 10101 | 1 gal. | Case of 4 | 40 lbs. | |